



## Flow Rates of Sparkler Filter Media

*(With water)*

Sparkler Grade	Material	Approx. Micron Retention	Approx. GPM/ft <sup>2</sup> @ 1.5 PSI.
<b>A</b>	<i>Cotton Rag</i>	<b>22</b>	16.15 gpm/ft <sup>2</sup>
<b>B</b>	<i>Cotton Rag</i>	<b>17</b>	14.15 gpm/ft <sup>2</sup>
<b>C</b>	<i>Bleached Wood Pulp</i>	<b>3</b>	12.15 gpm/ft <sup>2</sup>
<b>E</b>	<i>Unbleached Wood Pulp</i>	<b>12</b>	12.61 gpm/ft <sup>2</sup>
<b>P</b>	<i>Cotton-Cellulose Binder</i>	<b>25</b>	17.76 gpm/ft <sup>2</sup>
<b>Q</b>	<i>Rayon-Cellulose Binder</i>	<b>40</b>	17 gpm/ft <sup>2</sup>
<b>R</b>	<i>Cellulose-Polyester-Nylon-Latex Binder</i>	<b>15</b>	17.76 gpm/ft <sup>2</sup>